

Postle Industries • Cleveland, OH USA • Telephone: 216-265-9000 • Fax: 216-265-9030

Postalloy® 6710HD is modified Complex Niobium Chromium Carbide tubular hardfacing electrode, alloyed with a small addition of Molybdenum. The micro structure has very fine carbides which give improved wear, erosion and impact resistance over traditional Chromium Carbides. It is designed for applications that require more abrasion resistance than Postalloy® 215HD. The Carbide concentration is denser and slightly harder but less brittle than Postalloy® 215HD providing a better, more wear-resistant surface.

- Easy out-of-position weldability with the 1/4" diameter
- Excellent DC operation.
- High metal recovery - no slag to chip. Postalloy® 6710HD is over 90% efficient.
- Low amperage
- High deposition rates - up to 3 times faster than ordinary electrode
- Moisture resistant

Especificaciones

Tipo de producto

Flux-coated Tubular Electrode

Propiedades de la soldadura

Average Hardness: 62-65Rc

Maximum Deposit Thickness: 2 layers

Weld deposits will relief check-crack readily

Heat Resistant to: Excellent up to 1100°F (593°C)

Applications

Mining and quarry equipment

Dredge bucket lips and teeth

Scraper and grader blades

Crusher mantles and liners

Screw conveyors

Palm oil crusher rolls

Excellent final layer on manganese jaw crushers and swing hammers

The 1/4" size is ideal for vertical, edge and stringer beads

Postalloy® 6710HD Configuración de soldadura

Current: AC or DC Reverse Polarity

Diameter	Amps
1/4" (6.0mm)	70-130
3/8" (9mm)	150-180
1/2" (12mm)	180-325

Procedimiento de soldadura

Remove old hardfacing and any fatigued metal if weld spalling or cracking is a problem. Many steels can be hardfaced without special preheats, if the welding alloy used has relief checking. A low preheat of 150°F (66°C) may sometimes aid in weldability. Do not preheat austenitic manganese steels. The interpass temperature of austenitic manganese and most steels should be less than 500°F (260°C). Electrode angles should be slightly less than 90°. Do not apply more than two layers. A short arc length and stringer beads are recommended to reduce weld dilution.

Opciones de embalaje

Diámetro	Empaque estándar
1/4" (6.0mm)	Resealable Plastic Box
3/8" (9mm)	Resealable Plastic Box
1/2" (12mm)	Resealable Plastic Box

